

Tender specifications ADVANTAGE collection

Supply of Blustyle porcelain stoneware tiles for walls and floors.

Product characteristics

Blustyle full body porcelain stoneware tiles, unglazed (UGL), composed of a very fine mixture of quality clay with the addition of feldspar, quartz and kaolin, manufactured by dry pressing of atomized powders and subsequently sintered by industrial firing at temperatures above 1200°C.

The complete vitrification of the tiles allows for a compact, non-absorbent, frost-proof product, resistant to bending, impacts, staining, chemical attack and thermal shock.

Compliance with EN 14411-G / ISO 13006-G

The Advantage collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Blustyle in its plants and certified in accordance with UNI EN ISO 9001:2008.

The collection is manufactured in plants with UNI EN ISO 14001:2004 certified Environmental Management Systems (internationally recognized standard) and EMAS (Regulation 1221/09 - eco-management and audit community system). The collection helps to meet the criteria for obtaining LEED credits. The content of "pre-consumer" recycled material is 40%, as certified by a qualified external body (LEED V4 Regulations - MR Credit). The product contains no VOC (volatile organic compounds) and has obtained the GREENGUARD GOLD certification. The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the Advantage collection based on its Life Cycle Assessment (LCA).

Commercial description of the product							
Company	BLUSTYLE (Panariag	BLUSTYLE (Panariagroup Industrie Ceramiche S.p.A.)					
Collection	ADVANTAGE	ADVANTAGE					
Colours	Chalk, Greige, Silver	Chalk, Greige, Silver, Graphite					
	90X180cm NAT	90X180cm LAP					
	90x90 cm NAT	90x90 cm LAP					
Sizes	120x120 cm NAT	120x120 cm LAP					
	60x120 cm NAT	60x120 cm LAP	60x120 cm GRIP	60x120 cm SLATY			
	60x60 cm NAT	60x60 cm LAP	60x60 cm GRIP				
	30x60 cm NAT	30x60 cm LAP	30x60 cm GRIP				
Surfaces	NATURALE (NAT), LA	NATURALE (NAT), LAPPATA (LAP), GRIP, SLATY					
Edges	RECTIFIED (RTT)	RECTIFIED (RTT)					
Thickness	9mm – 20mm	9mm – 20mm					

















LEED







Tender specifications ADVANTAGE collection

Technical features

Product type: Porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

Technical features		Test method	Required values ISO 13006-G, EN 14411-G	Average values ADVANTAGE	
Water absorption		ISO 10545-3	≤ 0,5 %	0,05 %	
Breaking strength (S)		ISO 10545-4	≥ 1300 N	Thick. 9mm: 1800 N Thick. 20mm: 13600 N	
Modulus of rupture		ISO 10545-4	≥ 35 N/mm²	50 N/mm ²	
Deep abrasion resistance		ISO 10545-6	≤ 175mm³	145mm³	
Linear thermal expansion		ISO 10545-8	No provision	α ≤ 7·10 ⁻⁶ °C ⁻¹	
Stain resistance		ISO 10545-14	Class 3 Min.	5 RESISTENTE ≥ 3 (Chalk LAPPATA)	
Chemical re	esistance (*)	ISO 10545-13	As indicated by manufacturer	LA, HA RESISTANT	
Frost resistance		ISO 10545-12	No alteration	RESISTANT	
Dimensions	Lenght and width	ISO 10545-2	± 0,3 %, max ± 1 mm	COMPLIANT	
	Straightness of sides	ISO 10545-2	± 0,3 %, max ± 0,8 mm	COMPLIANT	
	Rectangularity	ISO 10545-2	± 0,3 %, max ± 1,5 mm	COMPLIANT	
	Warpage	ISO 10545-2	± 0,4 %, max ± 1,8 mm	COMPLIANT	
	Thickness	ISO 10545-2	± 5 %, max ± 0,5mm	COMPLIANT	
Slip resistance		DIN EN 16165 – Annex B	-	R10 (NAT) R11 (GRIP) R12 (SLATY)	
		DIN EN 16165 - Annex A	-	A+B (NAT) A+B+C (GRIP, SLATY)	
		BCR-TORTUS	-	μ > 0,40 (NAT, GRIP, SLATY)	
		ANSI A326.3	-	ID - DCOF ≥ 0,42 (dry) - LAPP/NAT IW - DCOF ≥ 0,42 (wet) - NAT IW+ - NAT (***) EW - GRIP/SLATY	
		BS 7976-2	-	PTV 36+ wet SI. 96 (NAT) PTV 36+ wet SI. 55 – sI 96 (GRIP, SLATY)	
		AS-NZS 4586	-	P3 (NAT) P4 (GRIP, SLATY)	
		UNE 41901 EX	-	Clase 1 (LAP) Clase 2 (NAT) Clase 3 (GRIP, SLATY)	
Shade variation		ANSI A 137.1	As indicated by manufacturer	V2	
Fire Reaction		EN 13823	CPR (UE) 305/2011, 2000/147/CE, UNI	Class A1 (wall)	
		EN 9239-1	EN 13501-1	Class A1 _{fl} (floor)	
Thermal conductivity		EN 12524	-	λ = 1,3 W/m °K	
Recommended minimum joint (**)		Indoor	-	2mm (RTT)	
		Outdoor		5-6mm approx.	

^(*) Excluding hydrofluoric acid and its derivatives.

^(***) With the exception of areas characterized by a higher risk of slipping (such as public showers, indoor swimming pools, etc.) for which a GRIP surface is recommended















LEED





^(**) The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.